

### **Listing of Claims**

1. (Currently Amended): A composition comprising a metal powder and an aromatic binder,  
  
    wherein said metal powder comprises an elemental metal that is a getter material; and  
  
    wherein said aromatic binder and said metal powder are mixed to form a feedstock for powder metallurgy forming techniques, said feedstock comprising less than approximately 40 vol% of said aromatic binder and no additional binders in an amount totaling greater than 10 vol%.
2. (Original): The composition as recited in Claim 1, wherein said powder metallurgy forming techniques are selected from the group consisting of injection molding, extrusion, compression molding, powder rolling, blow molding, laser forming, isostatic pressing, spray forming, and combinations thereof.
3. (Canceled)
4. (Previously Presented): The composition as recited in Claim 1, wherein said aromatic binder comprises a polycyclic aromatic.
5. (Original): The composition as recited in Claim 4, wherein said polycyclic aromatic is selected from the group consisting of naphthalene, anthracene, pyrene, phenanthrenequinone, and combinations thereof.
6. (Previously Presented): The composition as recited in Claim 1, wherein said aromatic binder comprises benzene and naphthalene.
7. (Canceled)

8. (Previously Presented): The composition as recited in Claim 1, wherein said aromatic binder comprises approximately 29% to 37% by volume of said feedstock.
- 9 – 23. (Canceled)
24. (Original): The composition as recited in Claim 1, wherein said metal powder comprises at least approximately 45% by volume of said feedstock.
25. (Original): The composition as recited in Claim 1, wherein said metal powder comprises approximately 45% to 95% by volume of said feedstock.
26. (Original): The composition as recited in Claim 1, wherein said metal powder comprises approximately 54.6% to 70% by volume of said feedstock.
27. (Previously Presented): The composition as recited in Claim 1, wherein said additional binder comprises a polymer.
28. (Canceled)
29. (Original): The composition as recited in Claim 27, wherein said polymer comprises a thermoplastic polymer.
30. (Original): The composition as recited in Claim 29, wherein said thermoplastic polymer is selected from the group consisting of ethylene vinyl acetate, polyethylene, butadiene-based polymers, and combinations thereof.
31. (Original): The composition as recited in Claim 27, wherein said polymer comprises a thermoset polymer.
32. (Original): The composition as recited in Claim 31, wherein said thermoset polymer is selected from the group consisting of polymethylmethacrylates, epoxies, unsaturated polyesters, and combinations thereof.

33. (Original): The composition as recited in Claim 27, wherein said polymer comprises a polymer mixture of at least one thermoplastic polymer and at least one thermoset polymer.
34. (Original): The composition as recited in Claim 33, wherein said thermoplastic polymer comprises approximately 2.1% to 5.1% by volume of said feedstock.
35. (Original): The composition as recited in Claim 33, wherein said thermoset polymer comprises approximately 2.3% by volume of said feedstock.
36. (Cancelled)
37. (Original): The composition as recited in Claim 33, wherein said polymer mixture comprises approximately 4.4% by volume of said feedstock.
38. (Previously Presented): The composition as recited in Claim 1, further comprising a surfactant.
39. (Original): The composition as recited in Claim 38, wherein said surfactant comprises a nonionic surfactant.
40. (Canceled)
41. (Previously Presented): A composition comprising an aromatic binder, a surfactant, system and a metal powder,  
wherein said metal powder comprises an elemental metal that is a getter material; and  
wherein said aromatic binder system, said surfactant, and said metal powder are mixed to form a feedstock for powder metallurgy forming techniques, and wherein said aromatic binder system comprises a surfactant in an amount up

~~to approximately 3% of the volume of said feedstock said surfactant comprising~~  
up to approximately 3% of the volume of said feedstock.

42. (Previously Presented): The composition as recited in Claim 41, wherein said surfactant comprises approximately 2.3% of the volume of said feedstock.
43. (Previously Presented): The composition as recited in Claim 1, further comprising a lubricant.
44. (Original): The composition as recited in Claim 43, wherein said lubricant is selected from the group consisting of organic fatty acids, metallic salts, solid waxes and combinations thereof.
45. (Original): The composition as recited in Claim 44, wherein said organic fatty acid is selected from the group comprising stearic acid, branched versions of stearic acid, substituted versions of stearic acid, and combinations thereof.
46. (Original): The composition as recited in Claim 44, wherein said metallic salts are selected from the group consisting of sodium stearate, calcium stearate, and combinations thereof.
47. (Original): The composition as recited in Claim 44, wherein said solid waxes are selected from the group consisting of microcrystalline waxes, paraffin waxes, caruba wax, and combinations thereof.
48. (Original): The composition as recited in Claim 43, wherein said lubricant comprises up to approximately 3% of the volume of said feedstock.
49. (Original): The composition as recited in Claim 43, wherein said lubricant comprises approximately 1.5% of the volume of said feedstock.

50. (Original): The composition as recited in Claim 1, further comprising at least one additional metal powder.
51. (Original): The composition as recited in Claim 50, wherein said additional metal powder comprises a sintering aid.
52. (Original): The composition as recited in Claim 51, wherein said sintering aid comprises silver.
53. (Original): The composition as recited in Claim 50, wherein said additional metal powder comprises an alloying powder.
- 54 – 151. (Canceled)